

FORESSO[®]

PRODUCT DATA SHEET

Introduction

Foresso is a handmade panel containing natural materials and as such no two panels will be the same. Ensure that you familiarise yourself with the possible variation and storage conditions to ensure optimal usage.

- Wood chips will vary in colour, tone, size, grain patterns, and will include knots and other character. This will vary within a sheet and between sheets, samples are indicative only and do not guarantee a timber colour.
- Chip density will vary within each sheet and between sheets. There will be areas with lesser and greater chip density.
- The sheet surface can contain small pores, indentations, or other small oddities as a result of our hand casting process. These are not considered defects and do not affect the performance of the surface.
- Sheets can vary in both thickness and flatness :
 - eg. A sheet may be 24mm in one area, and 23mm in another.
 - eg. Overall flatness along length or width can vary from sheet to sheet.
- Sheets should be stored at min 18°C and at a relative humidity of 35% - 65% wherever possible.
- If stored in cold condition Foresso sheets can bow or cup. This can occur in transit. Ensure that the sheets are given time to acclimatise to their environment and are stored as detailed above.

Composition

Material	Origin	Notes
End-grain Wood Chips	UK	Made in-house from British timber waste.
Wood Dust/Planing Waste	UK	Sourced from SMEs in the UK.
Mineral Powders	UK	50% sourced as waste.
0% VOC Bio-based Epoxy Resin	France	34% Biological Content.
Pigment	UK	98% Biological Content.
BB/BB Poplar Plywood	Spain	FSC & PEFC
Standard Hardwax Oil Finish	UK	Food-safe Natural Oil.

0203 302 7387 ~ help@foresso.co.uk ~ www.foresso.co.uk

Unit Q1, Hawthorns Industrial Estate, Middlemore Road, Birmingham B21 0BH
Limited Company Number 07333135 ~ VAT Registration Number GB127168708

Material Properties

Compressive Strength

Proportional Limit	10.31 MPa
Strain at Limit	2.17%
Turning Point	13.10 MPa
Strain at Turning Point	2.45%
Compression Modulus	892.46 MPa

Flexural Strength

Maximum Flexural Stress	77.06 MPa
Strain at Break	1.78%
Flexural Modulus	5498.68 MPa

Tolerances

Thickness	Foresso : 23.5mm +/- 0.5mm
	No-Chip : 20mm +/- 0.5mm
Length and Width (Sheets)	+/- 10mm. Sheets are supplied with a factory edge and can include slightly rounded corners/ends.
Length and Width (Flooring/CNC)	+/- 1mm

Certification

Fire Rating	Report reference	Result
BS 476 Part 7 (1997)	<i>Report ref WF438198</i>	Class 2
Slip Rating		
Dry <i>BS 7976-2:2002 + A1:2013</i>	<i>Report ref SP2598</i>	Low Slip Potential (52 PTV average - R12)
Wet <i>BS 7976-2:2002 + A1:2013</i>	<i>Report ref SP2598</i>	Moderate Slip Potential (26 PTV average - R10)

Finishes

Name	Standard	Description
Hardwax Oil	EN71-3: 2013	Food safe natural worktop oil with high resistance to scratching and staining.
High Traffic Furniture Lacquer	FIRA 6250:2005	Horizontal surfaces in Heavy/Severe contract usage
High Traffic Floor Lacquer	2004/42/EC	Medium to High traffic lacquer for wooden floors in commercial and insitutional environments.
Anti-slip Floor Lacquer	2004/42/EC BS 7976-2	Reduces slip potential in bars, schools, shopping centres, and all other high traffic public areas.
Fire Rated Lacquer	BS476 Part 6	Fire Propagation of Products Report Number: 315455
	BS476 Part 7	Surface Spread of Flame of Products Report Number: 315456
	EN13501-1	"Euro" Classification B-s1,d0 Report Number 333923
	FIRA 6250:2005	Horizontal surfaces in Heavy/Severe contract usage

0121 272 5537 ~ help@foresso.co.uk ~ www.foresso.co.uk

Unit Q1, Hawthorns Industrial Estate, Middlemore Road, Birmingham B21 0BH
Limited Company Number 07333135 ~ VAT Registration Number GB127168708